



Product information | TECHNICAL DATA SHEET FROSTED GLASS EFFECT PAINT

400 ml, 10.93 Oz, 310 g.

GENERAL DESCRIPTION

Translucent matt varnish for creating a frosted/glazed glass effect, formulated with a base of fast-drying thermoplastic acrylic resins.

CHARACTERISTICS

- Very fast-drying.
- Good adhesion.
- Translucent.
- Easy to apply and repaint.
- Water resistant.

APPLICATION

We recommend applying the product on glass in windows, doors, partitions, or on any transparent surface where you wish to obtain a frosted finish. It can be used as a decorative effect on mirrors or windows to create an engraved effect. Ideal for maintaining privacy in bathrooms, doctor's offices, changing rooms, etc. After application, the result can be cleaned with water during daily use without causing it to lose its properties.

- Glass.
- Some transparent plastics

INSTRUCTIONS FOR USE

- Shake the spray can well before use for about one minute after hearing the sound of the mixer ball.
- Apply to clean, dry surfaces. Clean surface with soap and water and allow to dry. On plastic, perform a prior test to observe the behavior of the product on the surface to be painted.
- We recommend applying two coats to obtain the frosted effect. To obtain good results, it is always better to apply two thin coats than one thick coat. The frosted effect appears as the product begins to dry. Can be repainted after 10 minutes with the same product or when it has a matt finish.
- Do not apply on surfaces in direct and prolonged contact with water, such as the inside of a shower screen.
- The product can be cleaned off gently with a cloth soaked in water. Limited resistance to abrasion.
- Invert the spray can to purge the valve after use. If the cap becomes clogged replace it with a new one.
- Do not apply to plugged in electronic equipment and use in well ventilated areas.
- Request safety data sheets

GENERAL DESCRIPTION

Binder type:	Thermoplastic acrylic
Color:	Translucent
Gloss (60°):	<5 matt
Dry to the touch (ASTM D-1640 ISO 1517):	10'
Total dry time (ASTM D-1640 ISO 1517)	2 h
Thickness of dry coat (ASTM D-823 ISO 2808):	<15 µ / coats
Theoretical performance:	2 m² for 400ml spray can
Solvent:	Butyl Acetate
Shelf life:	<5 Years (Well Stored)
Repainting:	After 10'
Paint resistance to head:	150°C
Application conditions:	Minimum atmospheric To: 8°C
	Surface temperature 5-45°C
	Max humidity 85% R.H.P

Montana Colors, S.L. P.I. Clot del Tufau - 08295 Sant Vicenç de Castellet BARCELONA

T.: +34 938 332 787 - montana@montanacolors.com - www.montanacolors.com

150121

IMAGE



65 mm

LID

Protects the valve. and the nozzle.

LABEL



Vidrio Esmerilado / Frosted Glass Effect EX014PR0410

CAP SYSTEM



PACKAGING

Nominal capacity 400 ml. Heat resistance of packaging: <50°C Propellant: DME

Box (6 units) 205 X 140 X 200 mm











^{*} Times may vary depending on thickness of coat.